Gas Resistant DPC Data Sheet



The Cordek Gas Resistant DPC is a polymeric DPC, designed for use in applications where combined damp proofing and gas protection is required. The DPC is robust and flexible, performing well under high compressive loads.

Key Features

- Excellent all round physical properties, including resistance to methane, carbon dioxide and radon
- Flexible, even at low temperatures
- · Good mortar adhesion properties
- Available in a range of widths to suit a variety of applications and helps to minimise wastage.

Installation

The Cordek Gas Resistant DPC should extend fully across the cavity and through the full thickness of the external wall, including pointing, applied rendering or other facing material. It must be laid on a wet, even bed of mortar with any perforations in adjacent courses of brickwork fully closed with mortar. All lap joints within the installation must have a minimum 150mm overlap and be completely sealed with the Cordek Double Sided Jointing Tape.

Storage & Handling

The Cordek Gas Resistant DPC should be stored in a cool, dry environment, away from direct sunlight.

For further information on the full range of VOC & Ground Gas Protection, please contact the Cordek technical team on 01403 799600, techsupport@cordek.com or consult our website at www.cordek.com.



Product Data

Typical Properties:

| Thickness | Nominal 1.0mm | | |
|---|--------------------------|--|--|
| Tensile Strength | 15 Nmm² | | |
| Elongation at Break | 600% | | |
| Dco ² (cm ² s ⁻¹) | 3.24 x 10 ⁻⁷ | | |
| Methane Permeability (k): | 1.16 × 10 ⁻¹⁴ | | |

| EN 1850-2 | - | | |
|------------|---|--|---|
| | | Pass/fail | Pass |
| EN 1848-2 | m | +/-5% | 20.0 |
| EN 1848-2 | m | +/-5% | 0.1 to 1.0 |
| EN 1848-2 | - | Pass/fail | Pass |
| EN 1849-2 | mm | +/-10% | 0.6 |
| EN 1849-2 | g/m² | +/-10% | 588 |
| EN 1928 | - | Pass/fail | Pass |
| EN 1928 | - | Pass/fail | Pass |
| EN 1928 | - | Pass/fail | Pass |
| EN 12691 | mm | >MLV | 250 |
| EN 495-5 | °C | MDV | -40 |
| EN 12310-1 | N | MDV | 270 |
| EN 1931 | g/(day.m²) | MDV | 0.5 |
| EN 12730 | Kg | >MLV | Pass 20 |
| EN 12317-2 | N/50mm | MDV | 153 |
| | EN 1848-2 EN 1849-2 EN 1849-2 EN 1928 EN 1928 EN 1928 EN 1928 EN 12691 EN 495-5 EN 12310-1 EN 1931 EN 12730 | EN 1848-2 m EN 1848-2 - EN 1849-2 mm EN 1849-2 g/m² EN 1928 - EN 1928 - EN 1928 - EN 12691 mm EN 495-5 °C EN 12310-1 N EN 1931 g/(day.m²) EN 12730 Kg | EN 1848-2 m +/-5% EN 1848-2 - Pass/fail EN 1849-2 mm +/-10% EN 1849-2 g/m² +/-10% EN 1928 - Pass/fail EN 1928 - Pass/fail EN 1928 - Pass/fail EN 1928 - MLV EN 12691 mm >MLV EN 495-5 °C MDV EN 12310-1 N MDV EN 1931 g/(day.m²) MDV EN 12730 Kg >MLV |

Issued: 03/2016

DISCLAIMER: Information contained within this 'Technical Data Sheet' is for guidance only, and it is intended for experienced construction industry workers. It contains summaries of aspects of the subject matter and does not provide comprehensive statements of construction industry practice.

As conditions of usage and installation are beyond our control we do not warrant performance obtained. Please contact us if you have any doubt as to the suitability of application. The information provided within this document is based on data and knowledge correct at the time of printing.

Cordek Ltd

Spring Copse Business Park, Slinfold, West Sussex RH13 0SZ, United Kingdom

Telephone (+44) 1403 799600 Fax (+44) 1403 791718 E-mail info@cordek.com



